


Features and Benefits

- 2.5W/m-K thermal conductivity
- Moderate compressibility
- Cost effective
- Electrically isolating



Typical Applications

- Notebook and desktop computers
- Memory modules
- Heat pipe assemblies
- HDDs and DVDs
- Flat-panel displays
- Telecommunication hardware

Optional Configurations

- Can be die-cut into specific dimensions


OP-8100 Spec 06 is a performance-improved derivative of the original OP-8100 gap filler. This special feature is benefited from a revised metal oxide filler matrix. It is electrically non-conductive and conforms to UL94 V0 standard. OP-8100 Spec06 is ROHS compliant and halogen free.

Properties	OP-8100 Spec 06	Test Method
Construction & Composition	Soft silicone elastomer	—
Color	Grey	Visual
Thickness Range /inch (mm)	0.01"~0.03" (0.25~0.75)	—
Standard Sheet Size	12" x 16"	—
Density /g.cm-3	2.65	—
Hardness /Shore 00	60	ASTM D2240
UL Flammability Rating	UL94 V0	—
Temperature Range /°C	-40~200°C	—
Thermal Conductivity W.m-1.K-1	2.5	ASTM D5470 (modified)
Breakdown Voltage / V	>4000V (Thickness ≥0.3mm) >4500V (Thickness ≥0.4mm) >5000V (Thickness ≥0.5mm)	ASTM D149
Shelf Life /Months	24	—

Please contact us for other requirements

Carrier Treatment	Criteria
Fiber Glass (FG)	Compulsory for ≤ 0.012" (0.3mm)
Rubberized Cloth (RC)	Not Recommended
Pressure Sensitive Adhesive (PSA)	Not Recommended
Detachable Adhesive (DA)	Not Recommended
Aluminum Foil (AL)	Not Recommended
Kapton (PI)	Not Recommended
Talc treatment (DAT)	Not Recommended

Product Code and Descriptions



SEM (North America) Inc.

Tel: +1 585-643-2000
 Fax: +1 585-427-7216
 Address: 1600 Lexington Ave., Suite 236A
 Rochester, NY 14606, USA

SEM Belgium bvba

+32 59 560 270
 +32 59 560 271
 Slijpesteenweg 28,
 8432 Middelkerke (Leffinge),
 Belgium


SEM (Far East) Ltd.

+852 2686 9872
 +852 2686 9728
 Unit 3, 3/F, Blk. A, New Trade Plaza,
 No. 6 On Ping St., Shatin, N.T.,
 Hong Kong

SEM (Dongguan) Ltd.

+86-769-8356 5686
 +86-769-8334 2028
 No.8 Qiaoxin Rd., Qiaotou
 Dongguan, Guangdong,
 China, 523525

Specifications and appearances may change without notice. All statements, technical information and recommendations herein are based on tests that we believed to be reliable, but the accuracy and completeness are not guaranteed. Before using, user should determine the suitability of the product for its intended use, and the user assumes all risks and liabilities whatsoever in connection therewith. Neither the seller nor the manufacturer shall be liable for any loss or damage, direct, incidental or consequential, including loss of profits or revenues arising from the use or inability to use the product. Any statements or recommendations shall have no effect unless contained in an agreement signed by authorized personnel of the seller and manufacturer.



SEM (North America) Inc.

+1 585-643-2000
 +1 585-427-7216
 1600 Lexington Ave., Suite 236A
 Rochester, NY 14606, USA

SEM Belgium bvba

+32 59 560 270
 +32 59 560 271
 Slijpesteenweg 28,
 8432 Middelkerke (Leffinge),
 Belgium

SEM (Far East) Ltd.

+852 2686 9872
 +852 2686 9728
 Unit 3, 3/F, Blk. A, New Trade Plaza,
 No. 6 On Ping St., Shatin, N.T.,
 Hong Kong

SEM (Dongguan) Ltd.

+86-769-8356 5686
 +86-769-8334 2028
 No.8 Qiaoxin Rd., Qiaotou
 Dongguan, Guangdong,
 China, 523525

Specifications and appearances may change without notice. All statements, technical information and recommendations herein are based on tests that we believed to be reliable, but the accuracy and completeness are not guaranteed. Before using, user should determine the suitability of the product for its intended use, and the user assumes all risks and liabilities whatsoever in connection therewith. Neither the seller nor the manufacturer shall be liable for any loss or damage, direct, incidental or consequential, including loss of profits or revenues arising from the use or inability to use the product. Any statements or recommendations shall have no effect unless contained in an agreement signed by authorized personnel of the seller and manufacturer.