


## **OP-8500 Spec 03**

## THERMALLY CONDUCTIVE GAP FILLER

#### **Features and Benefits**

- 2.8W/m-K thermal conductivity
- Good compressibility
- Naturally tacky
- Electrically isolating
- RoHS compliant
- Halogen-free



## **Typical Applications**

- Cooling component to the chassis, frame, or other type of heat spreader
- Mass storage devise
- Heat pipe assemblies
- RDRAM memory modules
- Motor control
- Telecommunication hardware

### **Optional Configurations**

Can be die-cut into specific dimensions


OP-8500 Spec 03 is a low hardness and fiberglass reinforced thermal gap filler which offers good thermal performance and exceptional conformability. This material conforms to surface irregularities under low application pressures. It is electrically non-conductive and naturally tacky. Additional adhesive is generally not required.

The proprietary formulation of OP-8500 Spec 03 is RoHS compliant and halogen-free, providing extra reassurance in applications where hazardous substances are forbidden.

Properties	OP-8500 Spec 03	Test Method
Construction & Composition	Soft silicone elastomer	
Color	Violet	Visual
Thickness Range /inch (mm)	0.01"~0.40" (0.254~10.16) in 0.01" (0.254) increments	
Standard Sheet Size	12" x 16"	
Density /g.cm <sup>-3</sup>	2.98	= :-
Hardness /Shore 00	15	ASTM D2240
Tensile Strength /psi	34	ASTM D412
UL Flammability Rating	UL94 V0	
Temperature Range /℃	-40~200℃	-
Thermal Conductivity/W.m <sup>-1</sup> .K <sup>-1</sup>	2.8	ASTM D5470 (modified)
Breakdown Voltage /V	>5000 (Thickness ≤ 0.04") >8000 (Thickness ≥ 0.05")	ASTM D149
Volume Resistivity /ohm.cm	8.0 x 10 <sup>13</sup>	ASTM D257
Dielectric Constant @ 1MHz	12.4	ASTM D150
Dielectric Strength / kV/mm	13.11	ASTM D149
Shelf Life /Months	24	

Carrier Treatment	Criteria	
Fiber Glass (FG)	Compulsory for ≤ 0.03" (0.75mm)	
Rubberized Cloth (RC)	Not Recommended	
Pressure Sensitive Adhesive (PSA)	Not Recommended	
Detachable Adhesive (DA)	Optional to ≥ 0.039" (1.0mm)	
Aluminum Foil (AL)	Optional to ≥ 0.039" (1.0mm)	
Kapton (PI)	Not Recommended	
Talc treatment (DAT)	Optional to all thickness	

## **Product Code and Descriptions**



#### SEM (North America) Inc.

Tel: Fax: Address: +1 585-643-2000 +1 585-427-7216 1600 Lexington Ave., Suite 236A, Rochester, NY 14606, USA

#### **SEM Belgium bvba**

+32 59 560 270 +32 59 560 271 Slijpesteenweg 28, 8432 Middelkerke (Leffinge), Belgium

#### SEM (Far East) Ltd.

+852 2686 9872 +852 2686 9728 Unit 3, 3/F, Blk A, New Trade Plaza, No. 6 On Ping St., Shatin, N.T., Hong Kong.


#### SEM (Dongguan) Ltd.

+86-769-8356 5686 +86-769-8334 2028 No.8 Qiaoxin Rd., Qiaotou Dongguan, Guangdong, China, 523525.



# **OP-8500 Spec 03**

## THERMALLY CONDUCTIVE GAP FILLER



SEM (North America) Inc.

Tel: Fax: Address: +1 585-643-2000 +1 585-427-7216 1600 Lexington Ave., Suite 236A Rochester, NY 14606, USA **SEM Belgium bvba** 

+32 59 560 270 +32 59 560 271 Slijpesteenweg 28, 8432 Middelkerke (Leffinge), Belgium SEM (Far East) Ltd.

+852 2686 9872 +852 2686 9728 Unit 3, 3/F, Blk A, New Trade Plaza, No. 6 On Ping St., Shatin, N.T., Hong Kong. SEM (Dongguan) Ltd.

+86-769-8356 5686 +86-769-8334 2028 No.8 Qiaoxin Rd., Qiaotou Dongguan, Guangdong, China, 523525.