

OU-809P is a high Compressible Gap Filler (Putty Type) with high performance thermally conductive compound and will not dry out. The surface consistency is excellent for filling surface irregularities as OU-809P is Sheet structure, which is convenient to use.

OU-809P provides a cost effective solution for application where rapid heat transfer from heat source to spreader is required.

OU-809P is RoHS compliant and halogen-free, offering extra reassurance in applications which hazardous substances are forbidden.

**Typical Applications**



- Heat source to spreader/sink in computer and peripherals
- Power conversion equipments
- Cooling components to the chassis, frame or other types of heat spreader
- Wireless communication hardware
- Automotive control units
- Power supply
- Audio and video component
- Micro processor

**Features and Benefits**

- 9.0W/m-K thermal conductivity
- Excellent thermal conductivity
- Never dries
- RoHS compliant
- Halogen-free

Typical Properties	OU-809P	Test Method
Construction & Composition	Silicone-based putty	—
Color	Gray	Visual
Thickness Range /inch (mm)	0.04"~0.40" (1.0~10.16) in 0.01" (0.254) increments	—
Standard Sheet Size(mm)	200 * 400	—
Density (g.cm <sup>-3</sup> )	3.4	—
Thermal Conductivity (W.m <sup>-1</sup> .K <sup>-1</sup> )	9	ASTM D5470 (modified)
Breakdown Voltage(KV/mm)	10	ASTM D149
Dielectric Strength (KVac/mm)	N/A	ASTM D149
Temperature Range (°C)	-40~180°C	—
UL Flammability Rating	UL94 V0	—
Shelf Life /Months	24	—

Please contact us for other special requirements



**SEM (North America) Inc.**

Tel: +1 585-643-2000  
 Fax: +1 585-427-7216  
 Address: 1600 Lexington Ave., Suite 236A  
 Rochester, NY 14606, USA

**SEM Belgium bvba**

+32 59 560 270  
 +32 59 560 271  
 Slijpesteenweg 28,  
 8432 Middelkerke (Leffinge), Belgium

**SEM (Far East) Ltd.**

+852 2686 9872  
 +852 2686 9728  
 Unit 3, 3/F, Blk A, New Trade Plaza,  
 No. 6 On Ping St., Shatin, N.T., Hong Kong.

**SEM (Dongguan) Ltd.**

+86-769-8356 5686  
 +86-769-8334 2028  
 No.8 Qiaoxin Rd., Qiaotou Dongguan,  
 Guangdong, China, 523525.

Specifications and appearances may change without notice. All statements, technical information and recommendations herein are based on tests that we believed to be reliable, but the accuracy and completeness are not guaranteed. Before using, user should determine the suitability of the product for its intended use, and the user assumes all risks and liabilities whatsoever in connection therewith. Neither the seller nor the manufacturer shall be liable for any loss or damage, direct, incidental or consequential, including loss of profits or revenues arising from the use or inability to use the product. Any statements or recommendations shall have no effect unless contained in an agreement signed by authorized personnel of the seller and manufacturer.